
BuzziTab Soft

Product Specification Sheet

This document contains technical information about the Buzzi Tab Soft








A chic reinterpretation of the classic acoustic panel

BuzziTab Soft is a playful acoustic treatment with exceptional sound-absorption capabilities. This chubby wall solution reinterprets the classic acoustic panel, suggesting that acoustics and design do pair. With its friendly appearance, well-rounded corners and edges, BuzziTab Soft breaks the hard surfaces and lines of a space. It lightens and softens walls—all while providing a retro look and feel. Play with perspectives and add depth of field with different models, available in various sizes and depths, and choose your favorite color combinations for a distinctive interior.

Design by BuzziSpace Studio

General

-  BuzziTab Soft Square | Rectangular
Wall mounted
-  Back: MDF
Filling: Acoustic foam
-  Cover: Fabric, Trevira CS+ | CS, Revive 1, Clara 2, Remix 3, Velvet, Hero, Tonus 4, Memory 2
-  Dry Use
-  Assembled

Acoustics



Absorption



Low tone



Mid tone



High tone


Content

Configurations	3
Fabrics	4
Fixing Systems	7
Dimensions	8
Acoustics	9

Configurations

BuzziTab Soft Square

Example composition (can be bought per piece)



Back: MDF
Filling: Acoustic foam
Cover: Fabric, Trevira CS+ | CS, Revive 1, Clara 2, Remix 3, Velvet, Hero, Tonus 4, Memory 2

SQ-4: W 59,5 cm H 59,5 cm D 4 cm
W 23.43" H 23.43" D 1.57"

SQ-8: W 59,5 cm H 59,5 cm D 8 cm
W 23.43" H 23.43" D 3.15"

SQ-12: W 59,5 cm H 59,5 cm D 12 cm
W 23.43" H 23.43" D 4.72"


SQ-4: 2,9 kg
6.39 lbs

SQ-8: 3,3 kg
7.28 lbs

SQ-12: 3,7 kg
8.16 lbs

BuzziTab Soft Rectangular

Example composition (can be bought per piece)



Back: MDF
Filling: Acoustic foam
Cover: Fabric, Trevira CS+ | CS, Revive 1, Clara 2, Remix 3, Velvet, Hero, Tonus 4, Memory 2

R-4: W 119 cm H 59,5 cm D 4 cm
W 46.85" H 23.43" D 1.57"

R-8: W 119 cm H 59,5 cm D 8 cm
W 46.85" H 23.43" D 3.15"

R-12: W 119 cm H 59,5 cm D 12 cm
W 46.85" H 23.43" D 4.72"


R-4: 5,8 kg
12.79 lbs

R-8: 6,6 kg
14.55 lbs

R-12: 7,4 kg
16.31 lbs

Fabrics

Fabric



Category A

Composition 70% Recycled Wool, 25% Recycled Polyacryl,
5% Recycled Other Fabrics

Weight 405 g/m² | 11.94 oz/yd²

Abrasion resistance 40.000 Martindale, 50,000 Wyzenbeek

Flammability EU: EN 1021.1/2006 | BS EN 1021.1/2006 (cigarette).
EN 1021.2/2006 | BS EN 1021.2/2006 (match)
USA: CAL TB 117 | ASTM E84 CLASS A


Fastness to light EU: 4 | USA 4

Fastness to rubbing EU: Wet 3-4 | Dry 4-5

Fastness to crocking USA: Wet 5 | Dry 5



Trevira CS+ | CS



Category A

Weight 420 g/m² | 12.39 oz/yd²

Composition 100% Polyester, Trevira CS

Abrasion resistance 100.000 Martindale, 90,000 Wyzenbeek

Flammability BS 5852 part II: CRIB 5 | BS 7176 Medium Hazard
USA: CAL TB 117 | M1 | B1 | EN 1021/1-2 | C1 |
IMO Res. A652 (16)

Fastness to light EU: 6 | USA 5


Fastness to rubbing EU: Wet 4-5 | Dry 4-5

Fastness to crocking USA: Wet 5 | Dry 5



Revive 1

kvadrat



Category A

Composition 100% recycled polyester FR

Weight 430 g/lin.m

Abrasion resistance 60.000 Martindale rubs, EN ISO 12947

Flammability EN 1021-1/2 | DIN 4102 B1 | Önorm B1/Q1
UNI 9175 1IM | US Cal. Tech. Bull. 117
IMO A.652 (16)


Fastness to light Note 5-7, ISO 105-B02

Fastness to rubbing (ISO) dry 5, wet 4-5

Pilling Note 4-5, EN ISO 12945



Velvet



Category B

Composition 100% PES

Weight 375 g/m² | 11.06 oz/yd²

Abrasion resistance > 100.000 Martindale


Fastness to light EU: 4-5

Fastness to rubbing EU: Wet 4 | Dry 4-5

Pilling EU: 4-5

Clara 2

kvadrat



Category B

Composition 92% new wool, 8% nylon

Weight 400 g/lin.m

Abrasion resistance 80.000 Martindale rubs, EN ISO 12947

Flammability EN 1021-1/2 | BS 5852, ignition source 2-3 | DIN 4102 B2
NF D 60 013 | UNI 9175 11M | US Cal. Tech. Bull. 117, Sec. E
NFPA 260 | IMO A.652(16)

Fastness to light Note 5-7, ISO 105-B02

Fastness to rubbing (ISO) dry 4-5, wet 4

Pilling Note 4, EN ISO 12945



Remix 3

kvadrat



Category B

Composition 90% new wool, 10% nylon

Weight 415 g/lin.m

Abrasion resistance 100.000 Martindale rubs, EN ISO 12947

Flammability EN 1021-1/2 | BS 5852 part 1
Önorm B1/Q1 | NF D 60 013 | UNI 9175, 11M
AS/NZS 1530.3 | Cal. Tech. Bull. 117-2013
NFPA 260 | IMO FTP Code 2010:Part 8

Fastness to light Note 5-7, ISO 105-B02


Fastness to rubbing (ISO) dry 4-5, wet 4

Pilling Note 4, EN ISO 12945



Hero

kvadrat



Category C

Composition 96% new wool, 4% nylon

Weight 580 g/lin.m

Abrasion resistance 45.000 Martindale rubs, EN ISO 12947

Flammability EN 1021-1/2 | DIN 4102 B2 | NF D 60 013
UNI 9175 11M | US Cal. Bull. 117-2013 | NFPA 260
IMO A.652 (16)

Fastness to light Note 5-6, ISO 105-B02

Fastness to rubbing (ISO) dry 4-5, wet 4-5

Pilling Note 3-4, EN ISO 12945



Tonus 4

kvadrat



Category D

Composition 90% new wool, 10% Helanca

Weight 665 g/lin.m

Abrasion resistance 100.000 Martindale rubs, EN ISO 12947


Flammability EN 1021-1/2 | BS 5852 part 1 | DIN 4102 B2
Önorm B1/Q1 | NF D 60 013 | UNI 9175 11M
US Cal. Bull. 117-2013 | NFPA 260 | IMO A.652 (16)

Fastness to light Note 5-7, ISO 105-B02

Fastness to rubbing (ISO) dry 3-5, wet 3-5

Pilling Note 3, EN ISO 12945





Category E

Composition 100% Trevira CS

Weight 700 g/lin.m

Abrasion resistance

35.000 rubs acc. to the Martindale method, EN ISO 12947

Flammability EN 1021-1/2 | DIN 4102 B1 | Önorm B1/Q1
NF D 60 013 | NF P 92 507 M1 | UNI 9175 1IM
UNI 9177 classe 1 | US Cal. Tech. Bull. 117
IMO A.652 (16)

Fastness to light Note 5-8, ISO 105-B02


Fastness to rubbing (ISO) dry 4-5, wet 4-5

Pilling Note 4, EN ISO 12945



Fixing Systems


Fixing System Wall (included)



BuzziTab Soft Fixing System.
4 pcs for BuzziTab Soft Square
4 pcs for BuzziTab Soft Rectangular
(horizontal or vertical mounting)

Dimensions BuzziTab Soft

BuzziTab Soft Square




SQ-12

12 cm
4.72"




SQ-8

8 cm
3.15"




SQ-4

4 cm
1.57"




BuzziTab Soft Rectangular




R-12

12 cm
4.72"




R-8

8 cm
3.15"



R-4


4 cm
1.57"



Acoustics

BuzziTab Soft

Absorption coefficient



Hz	α^s SQ-4/R4	α^s SQ-8/R8	α^s SQ-12/R12
125	0.11	0.35	0.58
250	0.30	0.70	1.00
500	0.60	1.00	1.00
1000	0.85	1.00	1.00
2000	1.00	1.00	1.00
4000	1.00	1.00	1.00

Absorption Values

SQ4/R4

α_w
(ISO 11654) **0.70**

NRC
(ASTM - C423) **0.70**

SAA
(ASTM-C423)

SQ8/R8

α_w
(ISO 11654) **0.95**

NRC
(ASTM - C423) **0.95**

SAA
(ASTM-C423)

SQ12/R12

α_w
(ISO 11654) **1.00**

NRC
(ASTM - C423) **1.00**

SAA
(ASTM-C423)

Glossary

All calculations are based on accredited lab measurements, official document available on Buzzi.Space

Definitions

α_w	Weighted absorption coefficient	(ISO 11654)
NRC	Noise reduction coefficient	(ASTM - C423)
SAA	Sound absorption average	(ASTM - C423)

Classification of sound absorbers NEN-EN-ISO 11654

A	0.90 0.95 1.0
B	0.80 0.85
C	0.60 0.65 0.70 0.75
D	0.03 0.55
E	0.15 0.25